

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims**

1. (Currently Amended) A carrier core material for an electrophotographic developing agent, comprising ferrite particles containing a ferrite component represented by the following formula (A):



wherein x, y and z are each expressed in % by mol and are numbers satisfying the conditions of  $40 \leq x \leq 60$ ,  $0.1 \leq y \leq 10$  and  $x+y+z=100$ , and

$ZrO_2$  in an amount of 0.01 to 5.0 parts by weight based on 100 parts by weight of the ferrite component, said  $ZrO_2$  not forming a solid solution with the ferrite component and said  $ZrO_2$  is finely dispersed in the ferrite component,

wherein the carrier core material has a magnetization, at  $1000(10^3/4\pi A/m)$ , of 65 to 85  $Am^2/kg$  and an electrical resistance, at an applied voltage of 1000 V, of  $10^5$  to  $10^9 \Omega$ .

2. (Original) The carrier core material for an electrophotographic developing agent as claimed in claim 1, wherein the ferrite particles further contain  $Bi_2O_3$  in an amount of 0.1 to 5.0 parts by weight.

3. (Previously Presented) The carrier core material for an electrophotographic developing agent as claimed in claim 1, wherein the surfaces of the ferrite particles have been oxidized.

4. (Original) The carrier core material for an electrophotographic developing agent as claimed in claim 3, wherein the ferrite particles having oxide layers on their surfaces have an electrical resistance, at an applied voltage of 1000 V, of  $10^6$  to  $10^{12} \Omega$ .

5. (Currently Amended) A coated carrier comprising:

a carrier core material which comprises ferrite particles containing

a ferrite component represented by the following formula (A):



wherein x, y and z are each expressed in % by mol and are numbers satisfying the conditions of  $40 \leq x \leq 60$ ,  $0.1 \leq y \leq 10$  and  $x+y+z=100$ , and

$ZrO_2$  in an amount of 0.01 to 5.0 parts by weight based on 100 parts by weight of the ferrite component, said  $ZrO_2$  not forming a solid solution with the ferrite component and said  $ZrO_2$  is finely dispersed in the ferrite component, and

a resin coating layer formed on the surface of the core material,

wherein the coated carrier has a magnetization, at  $1000(10^3/4\pi A/m)$ , of 65 to 85  $Am^2/kg$  and an electrical resistance, at an applied voltage of 1000 V, of not less than  $10^7 \Omega$ .

6. (Original) The coated carrier as claimed in claim 5, wherein the ferrite particles further contain  $Bi_2O_3$  in an amount of 0.1 to 5.0 parts by weight.

7. (Original) The coated carrier as claimed in claim 6, wherein the ferrite particles have oxide layers on their surfaces and have an electrical resistance, at an applied voltage of 1000 V, of  $10^6$  to  $10^{12} \Omega$ .

8. (Previously Presented) The coated carrier as claimed in claim 5, wherein the carrier core material is coated with a resin in an amount of 0.01 to 10 parts by weight based on 100 parts by weight of the carrier core material.

9. (Previously Presented) The coated carrier as claimed in claim 5, having an electrical resistance, at an applied voltage of 1000 V, of  $10^7$  to  $10^{13} \Omega$ .

10. (Currently Amended) The coated carrier as claimed in claim 5, wherein the coated carrier has an average particle diameter of 20 to 50  $\mu\text{m}$  and a 635-mesh passing ratio of not more than 10% by weight.

11. (Previously Presented) The coated carrier as claimed in claim 5, having a residual magnetization (Mr), at  $1000(10^3/4\pi\text{A/m})$ , of not more than  $5 \text{ Am}^2/\text{kg}$ , and a coercive force (Hc) of not more than  $20(10^3/4\pi\text{A/m})$ .

12. (Currently Amended) A two-component developing agent for electrophotography, comprising the coated carrier of claim 5 and toner particles having an average particle diameter of 3 to 15  $\mu\text{m}$ .

13. (Original) An image forming method comprising developing an electrostatic latent image formed by the use of an alternating electric field, with the two-component developing agent for electrophotography of claim 12.